

Trade name: **SIMONA® VERSADUR® HDPE black**

Revision: 02.11.2012

Date of printing: 18.12.2012

**SIMONA® VERSADUR® HDPE black**

Data sheet update, ,	02.11.2012
Density, g/cm <sup>3</sup> , D-792	0.970
Tensile Strength at yield, psi, D-638	4,500
Tensile Modulus, psi, D-638	240,000
Izod Impact (notched), ft.lbs./in., D-256	2.4
Coefficient of Thermal Expansion, in./in./°C, D-696	1.8 x 10 <sup>-4</sup>
Heat Deflection Temperature at 66 psi, °F,	175
Heat Deflection Temperature at 264 psi, °F,	118
Temperature Range, °F,	-58 to +176
FDA regulations 21 Chapter 1, part 177.2510 for contact with food stuffs, ,	yes

The data presented in this section are to be seen as a guide and may vary depending on the processing method and test specimen used. In general, the figures are averages of tests performed on extruded sheets with a thickness of 4 mm. In the case of sheets manufactured by means of pressing, testing is generally performed on sheets with a thickness of 20 mm. Deviations may be possible if sheets are not available in these specific thicknesses. In the case of backed sheets, all technical specifications relate to the non-backed base sheets. Please note that this information is not necessarily applicable to products that have undergone downstream processing. The suitability of a material for a specific area of application must be checked by the processor or end user. All technical specifications are provided only as a guide for planning purposes. They do not constitute a guarantee of specific properties or qualities. For further information, please contact our Technical Service Centre at [mail@simona-america.com](mailto:mail@simona-america.com).